

6⁵/₈ in 24 lb/ft S13Cr-95 (UNS S41425)

Box end finish: Cu-Plating Lubrication: API-Modified

Clearance: Standard Bevel: 45°

PIPE BODY CHARACTERISTICS

Nominal OD	6.625 in
Nominal ID	5.921 in
Min. Yield Strength	95 ksi
Nominal Wall Thickness	0.352 in
Minimum Wall Thickness	87.5 %
Drift	5.796 in

CONNECTION PROPERTIES

Coupling OD (nominal)	7.283 in
Coupling ID (nominal)	5.850 in
Make-up Loss	4.921 in
Coupling Length	10.866 in
Tension Efficiency	100 % of pipe
Compression Efficiency	100 % of pipe
Internal Pressure Efficiency	100 % of pipe
External Pressure Efficiency	100 % of pipe

CONNECTION PERFORMANCE

Tensile Yield Load	659 klb
Compression Yield Load	659 klb
Internal Yield Pressure	8 830 psi
External Pressure Resistance	6 310 psi
Max. Bending with API Sealability	20 °/100 ft
Max. Load on Coupling Face	397 klb

TORQUE VALUES

Minimum Make-up torque	11 420 ft·lb
Optimum Make-up torque	12 690 ft·lb
Maximum Make-up torque	13 950 ft·lb
Minimum Shoulder Torque	630 ft·lb
Maximum Shoulder Torque	8 880 ft·lb
Maximum Operational Torque	15 220 ft·lb

Connection qualified as per ISO 13679:2002 - CAL IV

