

6⁵/₈ in 20 lb/ft T95 (API 5CT)

Box end finish: Mang. Phosph. Lubrication: API-Modified

Clearance: Standard Bevel: 45°

PIPE BODY CHARACTERISTICS

Nominal OD	6.625 in
Nominal ID	6.049 in
Min. Yield Strength	95 ksi
Nominal Wall Thickness	0.288 in
Minimum Wall Thickness	87.5 %
Drift	5.924 in

CONNECTION PROPERTIES

Coupling OD (nominal)	7.283 in
Coupling ID (nominal)	5.976 in
Make-up Loss	4.921 in
Coupling Length	10.866 in
Tension Efficiency	100 % of pipe
Compression Efficiency	100 % of pipe
Internal Pressure Efficiency	100 % of pipe
External Pressure Efficiency	100 % of pipe

CONNECTION PERFORMANCE

Tensile Yield Load	545 klb
Compression Yield Load	545 klb
Internal Yield Pressure	7 230 psi
External Pressure Resistance	3 790 psi
Max. Bending with API Sealability	20 °/100 ft
Max. Load on Coupling Face	397 klb

TORQUE VALUES

Minimum Make-up torque	9 260 ft·lb
Optimum Make-up torque	10 290 ft·lb
Maximum Make-up torque	11 320 ft·lb
Minimum Shoulder Torque	520 ft·lb
Maximum Shoulder Torque	7 210 ft·lb
Maximum Operational Torque	12 350 ft·lb

Connection qualified as per ISO 13679:2002 - CAL IV

